

## Technické údaje:

Druh	Hustota v suchém stavu [kg/m <sup>3</sup> ]	Pevnost (MPa)		Součinitel tepelného prostupu (lambda) $\lambda_{D10}$ [W/m <sup>2</sup> x K]	Maximální hodnota součinitele U [W/m <sup>2</sup> x K]			
		v suchém stavu	6% vlhost		o tloušťce			
					42 cm	36 cm	30 cm	24 cm
600	550 ÷ 600	min. 5,0	min. 4,0	0,130	0,355	0,410	0,487	0,595
550	500 ÷ 550	min. 4,0	min. 3,0	0,115	0,315	0,365	0,432	0,530
450	400 ÷ 450	min. 2,5	min. 2,0	0,093	0,260	0,300	0,360	0,440

## Logistické údaje:

### Druh 450, 550, 600

P.č.	rozměry v cm	premium g ***		premium u / p / pu ****	
		Počet ks/paleta*	m <sup>3</sup>	Ilość szt / paleta *	m <sup>3</sup>
1.	Blok 42 x 24 x 49	36	1,78	30	1,48
2.	Blok 36 x 24 x 49	40	1,69	40	1,69
3.	Blok 30 x 24 x 49	48	1,69	40	1,41
4.	Blok 24 x 24 x 49	60	1,69	60	1,69
5.	Blok 18 x 24 x 49	72	1,52	-	-
6.	Blok 15 x 24 x 49	96	1,69	-	-
7.	Deska 12 x 24 x 49	120	1,69	-	-
8.	Deska 10 x 24 x 49	144	1,69	-	-
9.	Deska 8 x 24 x 49	180	1,69	-	-
10.	Deska 6 x 24 x 49	240	1,69	-	-
		Počet ks/ paleta **	m <sup>3</sup>		
11.	U-tvarovka 36 x 24 x 49	45	1,91	-	-
12.	U-tvarovka 30 x 24 x 49	54	1,91	-	-
13.	U-tvarovka 24 x 24 x 49	72	2,03	-	-

\* Paleta 120 x 100

\*\* Paleta 150 x 100

\*\*\* Gładki

\*\*\*\* Kapsou + perem a drążkou / hladká s kapsou / hladká s perem a drążkou